

Technical Data Sheet

Date of Issue 11/10/2016

Rev. 07_10/02/2023

2070

Painter's Flexi Masking Tape

**Product Description**

Painter's Flexi Masking Tape characterized by a high crepe paper backing with consistent stretch capabilities and a synthetic rubber resin solvent free adhesive. Its exceptional elongation makes it ideal for indoor masking and painting operations on curved surfaces following bends and round shapes with ease, saving time-consuming corrections of standard masking tapes. FSC® and PEFC certified masking tapes available on demand.

Features

- Excellent conformability on curved surfaces
- Suitable for most common solvent and water based paints
- Good paint anchorage
- Indoor removal time: 3 Days

Main Applications

- Painting operations (no UV exposure recommended)
- Round - shaped masking activities

Technical Data

	Metric	Imperial Units	Test Method
Total weight*	115 g/m ²	115 g/m ²	ISO 536
Total thickness*	280 µm	11 mils	Internal
MD tensile strength*	22 N/cm	12.6 Lbs/in	AFERA 5004/PSTC 131
MD elongation at break*	27 %	27 %	AFERA 5004/PSTC 131
Adhesion to steel plate*	0.8 N/cm	7.3 oz/in	AFERA 5001/PSTC 101
Adhesion to steel plate (Stretched)*	4.1 N/cm	37.5 oz/in	AFERA 5001/PSTC 101
Service temperature	up to 35°C	up to 95°F	

Backing material
High crepe paper

Type of adhesive
Synthetic rubber resin - solvent free

*Typical value

Available colour

Yellow

Technical Information and Product Use

All technical information and data above mentioned are provided to the best of our knowledge on the basis of our practical experience. Figures shown refer to average values only, based on tests carried out in conditioned laboratory and are not valid for specification. The company reserves the right to modify or change the products at any time without notice. The accuracy or completeness of such information is not guaranteed. The technical information, suggestions and other statements contained in this document have been compiled for your guidance and usage. PPM Industries reminds the user of the products to make sure that the product is used as per the instructions and suggestions provided. It is the user's sole responsibility to determine the suitability of the product in actual application under specific conditions.

Storage and Shelf Life

Suggested storage in dry area away from direct sunlight temperature should range from 59°F / 15°C to 77°F / 25°C with max relative humidity of 50%. Tape and jumbo roll should be used respectively within 12 months and 6 months from date of shipment. PPM Industries does not take responsibility for the defective material if is not stored and used in accordance with the conditions listed above.