

Technical Data Sheet

Date of Issue 01/03/2021

Rev. 04_12/02/2024

2040

Painter's Premium Masking Tape

**Product Description**

Painter's medium adhesion masking tape characterized by a semi crepe paper backing and a solvent borne rubber resin adhesive.

It is suitable for professional applications in Painting and Building industry, for masking and painting operations, and for spray painting activities at moderate temperature (max 80°C up to 30 min). FSC® and PEFC certified masking tapes available on demand.

Features

- Medium adhesion
- Excellent holding power
- Excellent contact on multiple surfaces
- Quick stick
- Good paint anchorage
- Suitable for most common water and solvent base paints
- Indoor removal time: 5 Days

Main Applications

- Professional masking, painting and building operations (no UV exposure recommended)
- Spray painting operations at medium-high temperature (max 80°C up to 30 min)

Technical Data

| | Metric | Imperial Units | Test Method |
|--------------------------|---------------------|---------------------|---------------------|
| Total weight* | 93 g/m ² | 93 g/m ² | ISO 536 |
| Total thickness* | 120 µm | 4.7 mils | Internal |
| MD tensile strength* | 38 N/cm | 21.7 Lbs/in | AFERA 5004/PSTC 131 |
| MD elongation at break* | 7% | 7% | AFERA 5004/PSTC 131 |
| Adhesion to steel plate* | 2.0 N/cm | 18.3 oz/in | AFERA 5001/PSTC 101 |
| Service temperature | up to 80°C | up to 176°F | |

Backing material

Saturated crepe paper

Type of adhesive

Natural rubber

*Typical value

Available colour

White Yellow Brown

Technical Information and Product Use

All technical information and data above mentioned are provided to the best of our knowledge on the basis of our practical experience. Figures shown refer to average values only, based on tests carried out in conditioned laboratory and are not valid for specification. The company reserves the right to modify or change the products at any time without notice. The accuracy or completeness of such information is not guaranteed. The technical information, suggestions and other statements contained in this document have been compiled for your guidance and usage. PPM Industries reminds the user of the products to make sure that the product is used as per the instructions and suggestions provided. It is the user's sole responsibility to determine the suitability of the product in actual application under specific conditions.

Storage and Shelf Life

Suggested storage in dry area away from direct sunlight temperature should range from 59°F / 15°C to 77°F / 25°C with max relative humidity of 50%. Tape and jumbo roll should be used respectively within 12 months and 6 months from date of shipment. PPM Industries does not take responsibility for the defective material if is not stored and used in accordance with the conditions listed above.